

Sliptest Australia Pty Ltd NATA Accreditation No: 15374 11 Fuchsia Way, Gaven, QLD, 4211 sales@sliptest.com.au www.sliptest.com.au 1300 754 783

Hurford Wholesale - HM WALK - AMERICAN WHITE OAK

26 Sep 2017

Slip Resistance Classification of New Pedestrian Surfaces - AS4586:2013 Appendix A

Date Tested:	26 Sep 2017				
Test Report Number:	KO260917-8				
Client Name & Address:	Hurford Wholesale - 400 Jacobs Well Road, STAPYLTON QLD 4207				
Product Tested :	HM WALK - AMERICAN WHITE OAK				
Wet Pendulum Test carried out using :	Slider 96 (4S) Rubber slider				
Record ambient temperature (°C)	23				
Testing Officer :	Kathryn Ording - Munro-Stanley Portable Skid Tester #1133 - 30.08.17				
Testing Officer Signature					

Test Results:

No. of Samples	Sample No.	Swing 1	Swing 2	Swing 3	Swing 4	Swing 5	Mean BPN of last 3 swings :	Surface Picture
5	Plank 1	40	40	40	40	40	40	
	Plank 2	44	44	42	42	41	42	
	Plank 3	40	39	39	38	38	38	
	Plank 4	41	40	40	40	40	40	
	Plank 4	42	41	41	41	41	41	Sliptest

Mean BPN Slip Resistance Value (SRV)	40
CLASSIFICATION using Slider 96 (4S Slider)	P3 - 35 - 44

Accedited for Compliance with ISO/IEC 17025. The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited. Sliptest Australia Ptv. Ltd. performed this on site test with reference to the following Australian Standard testing criteria, of AS 4586:2013 Classification of new pedestrian surface materials. Appendix A – Wet Pendulum Test Method and Hand Book HB 198: 2014 with reference to AS/NZS 4663: 2004 Slip Resistance measurement of existing pedestrian surfaces and HB 197: 1999. These results to not account for Future Wear, Maintenance or Contamination of this surface once in-situ.

Hurford Wholesale - HM WALK - AMERICAN WHITE OAK

CONFIDENTIAL

Issue: TR4586:V1.2017

Version: 46