

**ATTAR TEST REPORT NUMBER:15/8788.15**
Replacement of ATTAR Test Report No. 15/8788.8The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.
Accredited for compliance with ISO/IEC 17025.
Accreditation Number: 2735

21 April 2015

Total Pages: 2**WET PENDULUM SLIP RESISTANCE**

Job No: M15/8788

Prepared for:	Premium Floors Australia 7/14 Rodborough Road FRENCH'S FOREST NSW 2086					
Attention:	Kendall Waller					
Test Site:	Test Slip Australia Pty Ltd, Beaumont Hills, NSW.					
Test Date:	26 March 2015					
Test Specimens, Size & Quantity:	Unilin Engineered wood floor Matt, 270x1820 mm, 5 off supplied.					
Sampling & Direction of Testing:	Sampling conducted by client. Test parallel to the direction of manufacture.					
Test Personnel:	Clark Ahearn					
Preparation:	Washed with water and pH neutral detergent, rinsed with water, then dried.					
Fixed/Unfixed:	Fixed.					
Air Temperature:	22°C					
Test Equipment:	Wessex Skid Resistance Tester (Pendulum) Serial Number SK 1818, Calibrated 29/07/2014.					
Test Standard:	AS 4586: 2013 Slip resistance classification of new pedestrian surface materials – Appendix A.					
Slider Rubber:	Slider 96 Batch No. #55 prepared on P400 & 3µm lapping film.					
Classification Criteria:	Refer to Classification Criteria, attached as Appendix 1.					
British Pendulum Number	Specimen Number					SRV
	1	2	3	4	5	
	36	33	37	35	32	35
Classification:	P3					

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTARDaniel King BEng (Mats) Hons,
Materials and Testing Engineer
Approved Signatory

This report may not be reproduced except in its entirety.




Figure 1: Unilin Engineered wood floor Matt.
Highlighted area indicates direction of test.