

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-005088
Issue Date : 17/01/2023
Print Date : 30/01/2023

Sample Description Clients Ref : "Hybrid Shield"
Hybrid flooring plank with acoustic underlay
Colour : Coffee Bean Trivia
End Use : Flooring
Nominal Composition : Wood, Wax Composite
Nominal Mass per Unit Area/Density : 880kg/m3
Nominal Thickness : 10mm



287630

62201

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-005088
Issue Date : 17/01/2023
Print Date : 30/01/2023

AS 4586-2013 Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials Wet Pendulum Test Method

Date of Testing 17/01/2023
Test Temperature (20±5degC) 22 °C
Sample Preparation Sample washed with pH neutral detergent then dried .
Test Direction Length
Fixed/Unfixed Unfixed
Slider No 96 Batch No 15
Length 1 2 3 4 5 SRV
British Pendulum 32 33 32 34 31 32
Number
Classification P2

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 21/09/2021
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

287630

62201

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR