

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-000571
Issue Date : 11/04/2022
Print Date : 27/05/2022

Sample Description Clients Ref : "Australian Engineered Flooring"
Engineered timber flooring planks
End Use : Flooring
Nominal Thickness : Approx 15mm



268981

56832

Page 1 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-000571
Issue Date : 11/04/2022
Print Date : 27/05/2022

ASTM D5116-2017

Standard Guide for Small Scale Environmental Chamber Determination of Organism Emission from Indoor Materials/Products

Seal and Test Underside of the test specimen is placed on an inert glass plate to determine exclusively the emission of the upper surface, sealing the edge with aluminium foil in 10mm width

Test Specimen Size 555x135, 4 pieces mm
Test Time 24 Hrs
Test Temperature 23 degC
Test Humidity 50%
Loading Factor 0.30m2m3
Air Exchange 1 / h

	Cas No	Test Result Concentration (24 Hour) mg/m3	Emission Factor Test Result (24 Hour) mg/m2.h
Formaldehyde	50-00-0	0.027	0.089

Date of Testing 08/04/2022

268981

56832

Page 2 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-000571
Issue Date : 11/04/2022
Print Date : 27/05/2022

Remarks:

1. Formaldehyd and acetaldehyde were detected using HPLC method with ultraviolet detector, whereas other VOC's substances were detected by Gas chromatography/Mass spectrometry method.
2. In this Gas chromatography/Mass spectrometry method, the scan mode of SIM was employed for caprolactum detection, and TIC for others.

Tested by AWTA-JSIC JinAo Testing Co Limited - China.

Report Number: JA221099

268981

56832

Page 3 of 3

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR